

## **TEROSON SI 9150**

October 2016

#### **PRODUCT DESCRIPTION**

TEROSON SI 9150 provides the following product characteristics:

Technology	Neutral curing
Product Type	Sealant
Application	Assembly
Appearance	Black

TEROSON SI 9150 is a solvent free, high viscosity, one-component sealant based on neutral curing silicone rubber which cures by reaction with moisture to a rubber-like firm mass.

Due to the good sag resistance, the product can be applied to both horizontal and vertical surfaces.

The skin formation and curing times are dependent on humidity and temperature, and the curing time also depends on joint depth.

By increasing the temperature and moisture these times can be reduced; low temperature as well as low moisture retard the process

After curing, TEROSON SI 9150 demonstrates excellent resistance against oil and other liquid media during the occuring temperatures.

Both surfaces have full metal-to-metal contact.

Tolerances and surface roughness will be equalised by the pasty sealant which cures to an elastic silicone rubber based gasket: formed-in-place gasket without relaxing which makes any later tightning of the screws unnecessary.

On parts which are only mounted after curing of TEROSON SI 9150 the material acts like a standard gasket also bridging larger tolerances.

#### Advantages:

1. Because TEROSON SI 9150 gets its final shape only after mating of the surfaces it does not show the typical disadvantages of standard gaskets arising even prior to applicati on:

Ageing - Contraction - Deformation - Breaking

- 2. One sealant instead of numerous gaskets simplifies inventory- particularly in the maintenance field.
- 3. Gaskets require a certain thickness, but cannot guarantee a good, effective compression seal despite their thickness and large area if the surfaces are too rough. They rather require additional liquid sealants like Atmosit or others. When using TEROSON SI 9150 the top of the rough metal surfaces have metal-to-metal contact while the silicone sealant solidly fills the low points or voids thus sealing 100%.
- 4. Gaskets will relax eventually causing torque loss. No relaxing with TEROSON SI 9150 because of the metalto-metal contact. Relative movements will be eliminated by the elasticity.

#### **Application Areas:**

TEROSON SI 9150 is used as Formed-in-Place-Gasket (FIPG) for replacing traditional gaskets (e.g. those made from asbestos, paper, rubber, cork, etc.), for sealing jobs with a spacer function or as an ideal seal with optimum surface contact on housings or housing lids, particularly for increased temperatures.

Typical application areas are, for instance, oil pan covers, thermostat housings, valve covers, axle covers, etc.

#### **TECHNICAL DATA**

Color:	black
Consistency:	paste
Density:	approx. 1.1 g/cm <sup>3</sup>
Solids:	100%
Curing mechanism:	humidity curing
Curing system:	oxime
Skin formation time:	approx. 5 to 10 min(s)
(DIN 50014 standard climate:	23°C, 50% rh)
Shore-A-hardness (DIN 53505):	~40
In service temperature range:	-40 to 200°C (depending on medium)
Short exposure (up to 1h):	220°C

Short exposure (up to 1h):

#### **DIRECTIONS OF USE**

#### Preliminary statement:

Prior to use it is necessary to read the Material Safety Data Sheet for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed.

#### **Pre-Treatment:**

The substrates to be sealed must be clean, dry, oil and grease free; a thin oil film, however, does not interfere the tightness. In most cases wiping off with dry and clean cloth is sufficient.

#### Application:

TEROSON SI 9150 is applied as a thin bead to one surface, the other surface is matched and srewed according to regulations.

The sealant is spread by pressing and thus fills all low points whereas some points have metal-to-metal contact.

Finally the sealant film cures to a rubber elastic gasket.

Matching of the parts should occur within 15 minutes unless a complete curing is desired. Heavier skin formation can cause problems in a tight seal.



Matching of the parts can also be made after curing assuming an even surface layer. In those cases TEROSON SI 9150 will act as a gasket bonded to the substrate. Parts sealed in such a way can easily be dismounted.

TEROSON SI 9150 can be directly applied from cartidges employing standard air or hand operated guns. TEROSON recommends the use of:

- Teleskop Pistol Power-Line Art.-No. 141.84 S

- Teroson Staku Hand Pressure Pistol Art.-No. 167.65 Y

In the case of compressed air application a pressure of 2 - 5 bar is required.

#### STORAGE

Frost-Sensitive	No
Recommended Storage Temperature, °C	15 to 20
Shelf-life (in unopened original packaging),	12
months	

#### **Classification:**

Please refer to the corresponding **safety data sheets** for details on:

Hazardous Information Transport Regulations Safety Regulations Waste Disposal

### ADDITIONAL INFORMATION Disclaimer:

#### Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

#### In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

### In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

# In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference N/A

Henkel Corporation USA Madison Heights, MI 48071 Phone: +1-248-583-9300 For more information, please contact us on www.henkel.com